



**Technical and Test Institute  
for Construction Prague**  
Prosecká 811/76a  
190 00 Prague  
Czech Republic  
eota@tzus.cz



## European Technical Assessment

**ETA 14/0464  
of 27/05/2016**

(English language translation, the original version in Czech language)

### *I General Part*

**Technical Assessment Body issuing the  
ETA and designated according to Article  
29 of the Regulation (EU) No. 305/2011:  
Trade name of the construction product  
Product family to which the construction  
product belongs**

**Manufacturer**

**Manufacturing plant(s)**

**This European Technical Assessment  
contains**

**This European Technical Assessment is  
issued in accordance with regulation (EU)  
No. 305/2011 on the basis of  
This European Technical Assessment  
replaces:**

Technical and Test Institute for Construction  
Prague

#### **FAST S**

Product area code: 4  
External Thermal Insulation Composite  
Systems with rendering on expanded  
polystyrene EPS for the use as external  
insulation to walls of buildings.

P.W. FAST Sp. z o.o.  
ul. Folszowa 112  
65-751 Zielona Gora  
Republic of Poland  
www.fast.zgora.pl

P.W. FAST Sp. z o.o.  
ul. Folszowa 112  
65-751 Zielona Gora  
Republic of Poland

26 pages including 3 Annexes which form an  
integral part of this Assessment.

Annex No. 4 Control Plan contains  
confidential information and is not included in  
the European Technical Assessment when  
that Assessment is publicly available.

ETAG 004, edition 2013, used as European  
Assessment Document (EAD)

ETA 14/0464 valid from 30/12/2014

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full (excepted the confidential Annex(es) referred to above). However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body - Technical and Test Institute for Construction Prague. Any partial reproduction has to be identified as such.

# 1 Technical description of the product

## 1.1 Definition and composition of the kit

This product is an ETICS (External Thermal Insulation Composite System) with rendering - a kit comprising components which are factory-produced by the manufacturer or component suppliers. The ETICS manufacturer is ultimately responsible for all components of the ETICS specified in this ETA.

The ETICS kit comprises a prefabricated insulation product of expanded polystyrene (EPS) to be bonded or mechanically fixed onto a wall. The methods of fixing and the relevant components are specified in the table below. The insulation product is faced with a rendering system consisting of one or more layers (site applied), one of which contains reinforcement. The rendering system is applied directly to the insulating panels, without any air gap or disconnecting layer.

The ETICS may include special fittings (e.g. base profiles, corner profiles ...) to treat details of ETICS (connections, corners, parapets, sills ...). Assessment and performance of these components is not addressed in this ETA, however the ETICS manufacturer is responsible for adequate compatibility and performance within the ETICS when the components are delivered as a part of the kit.

### Composition of the ETICS

Table No. 1

	Components	Coverage (kg/m <sup>2</sup> )	Thickness (mm)
<b>Insulation products with associated methods of fixing</b>	<b>Bonded ETICS (fully or partially bonded) with supplementary anchors. National application documents shall be taken into account).</b>		
	<ul style="list-style-type: none"> <li>• Insulation product: EPS according to EN 13163: 2013 see Annex No. 1 for product characteristics</li> </ul>	/	50 to 250
	<ul style="list-style-type: none"> <li>• Adhesives:                             <ul style="list-style-type: none"> <li>- <b>FAST Normal S</b> (cement based powder requiring addition of water 0.22 l/kg)</li> <li>- <b>FAST Specjal/FAST Specjal M</b> (cement based powder requiring addition of water 0.20 l/kg)</li> <li>- <b>FAST Specjal DS</b> (ready to use paste)</li> </ul> </li> </ul>	3.0 to 5.0 (dry)	/
		2.0 – 3.0	

	Components	Coverage (kg/m <sup>2</sup> )	Thickness (mm)
<b>Insulation products with associated methods of fixing</b>	<b>Mechanically fixed ETICS with anchors and supplementary adhesive (see Cl. 3.4.4 and Annex No. 2 for possible associations EPS/anchors)</b>		
	<ul style="list-style-type: none"> <li>• Insulation product: EPS according to EN 13163: 2012 see Annex No. 1 for product characteristics</li> </ul>	/	50 to 250
	<ul style="list-style-type: none"> <li>• Supplementary adhesives: <ul style="list-style-type: none"> <li>- <b>FAST Normal S</b> (cement based powder requiring addition of water 0.22 l/kg)</li> <li>- <b>FAST Specjal/FAST Specjal M</b> (cement based powder requiring addition of water 0.20 l/kg)</li> <li>- <b>FAST Specjal DS</b> (ready to use paste)</li> </ul> </li> </ul>	3.0 to 5.0 (dry)	/
	<ul style="list-style-type: none"> <li>• Anchors see Annex No. 2 for individual product characteristics. In addition to the following list, other anchors can be used provided that they comply with the requirements introduced in the Annex 2. <ul style="list-style-type: none"> <li>- <b>ejotherm STR U. STR U 2G</b> plastic screw-in anchors</li> <li>- <b>ejotherm NT U</b> plastic nailed-in anchors</li> <li>- <b>ejotherm NTK U</b> plastic nailed-in anchors</li> <li>- <b>EJOT SDM-T plus</b> plastic screw-in anchors</li> <li>- <b>Ejot H1 eco</b> plastic nailed-in anchors</li> <li>- <b>EJOT H3</b> plastic nailed-in anchors</li> <li>- <b>KOELNER TFIX-8M</b> plastic nailed-in anchors</li> <li>- <b>KOELNER TFIX-8S. TFIX-8ST</b> plastic screw-in anchors</li> <li>- <b>KOELNER KI-10N</b> plastic nailed-in anchors</li> <li>- <b>KOELNER KI-10NS</b> plastic screw-in anchors</li> <li>- <b>BRAVOLL PTH-KZ 60/8-La</b></li> <li>- <b>BRAVOLL PTH 60/8-La</b> plastic nailed-in anchors</li> </ul> </li> </ul>	<p>ETA-04/0023</p> <p>ETA-05/0009</p> <p>ETA-07/0026</p> <p>ETA-04/0064</p> <p>ETA-11/0192</p> <p>ETA-14/0130</p> <p>ETA-08/0336</p> <p>ETA-11/0144</p> <p>ETA-07/0221</p> <p>ETA-05/0055</p>	

	Components	Coverage (kg/m <sup>2</sup> )	Thickness (mm)
	<ul style="list-style-type: none"> <li>- <b>WKRET-MET LFN 8. LFM 8</b> plastic nailed-in anchors</li> <li>- <b>WKRET-MET LFN 10. LFM 10</b> plastic nailed-in anchors</li> <li>- <b>WKRET-MET LTX 10. LMX 10</b> plastic nailed-in anchors</li> <li>- <b>KEW TSD 8</b> plastic nailed-in anchors</li> <li>- <b>fischer TERMOZ 8N. 8 NZ</b> plastic nailed-in anchors</li> <li>- <b>fischer TERMOZ 8U. 8 UZ</b> plastic screw-in anchors</li> <li>- <b>Hilti XI-FV</b> plastic gun-nailed anchors</li> <li>- <b>Hilti SX-FV</b> plastic screw-in anchors</li> <li>- <b>Hilti SD-FV8</b> plastic nailed-in anchors</li> <li>- <b>Hilti SDK-FV 8</b> plastic nailed-in anchors</li> <li>- <b>Hilti D-FV. D-FV T</b> plastic screw-in anchors</li> </ul>	<p>ETA-06/0080</p> <p>ETA-06/0105</p> <p>ETA-08/0172</p> <p>ETA-04/0030</p> <p>ETA-03/0019</p> <p>ETA-02/0019</p> <p>ETA-03/0004</p> <p>ETA-03/0005</p> <p>ETA-03/0028</p> <p>ETA-07/0302</p> <p>ETA-05/0039</p>	
<b>Base coat</b>	<ul style="list-style-type: none"> <li>• <b>FAST Specjal/FAST Specjal M</b> (cement based powder requiring addition of water 0.20 l/kg)</li> </ul>	3.0 to 5.0 (dry)	3.0 - 5.0
<b>Reinforcement</b>	<ul style="list-style-type: none"> <li>• Standard mesh applied in one or two layers see Annex No. 3 for product characteristics:</li> <li>- <b>AKE 145A / R 117 A101</b></li> <li>- <b>AKE 160 / R 131 A101</b></li> <li>- <b>117S</b></li> <li>- <b>SECCO E 145</b></li> <li>- <b>SECCO E 160</b></li> <li>- <b>REDNET E 145</b></li> <li>- <b>REDNET E 160</b></li> <li>- <b>Valmieras SSA-1363-160</b></li> </ul>	/	/

	Components	Coverage (kg/m <sup>2</sup> )	Thickness (mm)
Key coat	- <b>FAST Grunt M</b> ready to use liquid	0.35	/
	- <b>FAST Grunt S-T</b> ready to use liquid		
Finishing coats	<ul style="list-style-type: none"> <li>• Powder – mineral binder: <ul style="list-style-type: none"> <li>- <b>FAST Baranek</b> spotted structure (particle size 2.0; 2.5; 3.0 mm). powder requiring addition of water 0.20 - 0.22 l/kg</li> <li>- <b>FAST Kornik</b> ribbed structure (particle size 2.0; 3.0 mm). powder requiring addition of water 0.20 - 0.22 l/kg</li> <li>- <b>FAST WD (WET. DRY Dash)</b> surface treated by crushed stones powder requiring addition of water 0.18 l/kg</li> <li>- <b>FAST MS</b> powder requiring addition of water 0.22 – 0,28 l/kg</li> </ul> </li> </ul>	2.2 to 3.5	Regulated by particle size
	<ul style="list-style-type: none"> <li>• Ready to use paste – binder based on silicate: <ul style="list-style-type: none"> <li>- <b>FAST Baranek S</b> spotted structure (particle size 1.0; 1.5; 2.0 mm)</li> <li>- <b>FAST Kornik S</b> ribbed structure (particle size 2.0; 3.0 mm)</li> </ul> </li> </ul>	1.7 to 3.5	Regulated by particle size
	<ul style="list-style-type: none"> <li>• Ready to use paste – binder based on acrylic: <ul style="list-style-type: none"> <li>- <b>FAST Baranek A</b> spotted structure (particle size 1.0; 1.5; 2.0 mm)</li> <li>- <b>FAST Akryl +</b> spotted structure (particle size 1.0; 1.5; 2.0 mm)</li> <li>- <b>FAST Kornik A</b> ribbed structure (particle size 2.0; 3.0 mm)</li> <li>- <b>FAST Granit</b> mosaic structure (particle size 1.5 mm)</li> </ul> </li> </ul>	1.7 to 3.5	Regulated by particle size
	<ul style="list-style-type: none"> <li>• Ready to use paste – binder based on siloxane: <ul style="list-style-type: none"> <li>- <b>FAST Baranek SI</b> spotted structure (particle size 1.0; 1.5; 2.0 mm)</li> <li>- <b>FAST Kornik SI</b> ribbed structure (particle size 2.0; 3.0 mm)</li> </ul> </li> </ul>	1.7 to 3.5	Regulated by particle size

	Components	Coverage (kg/m <sup>2</sup> )	Thickness (mm)
<b>Finishing coats</b>	<ul style="list-style-type: none"> <li>• Ready to use paste – binder based on silicone: <ul style="list-style-type: none"> <li>- <b>FAST Baranek SIL</b> spotted structure (particle size 1.0; 1.5; 2.0 mm)</li> <li>- <b>FAST Kornik SIL</b> ribbed structure (particle size 2.0; 3.0 mm)</li> </ul> </li> </ul>	<p>1.7 to 3.5</p> <p>1.7 to 3.5</p>	Regulated by particle size
<b>Key coats to be used under protective coats</b>	<b>Only to be used with finishing coats FAST Baranek. FAST Kornik and FAST MS</b>		
	<ul style="list-style-type: none"> <li>- <b>FAST Grunt S</b> to be used under silicate protective coat ready to use liquid</li> <li>- <b>FAST Grunt SIL</b> to be used under silicone protective coat ready to use liquid</li> <li>- <b>FAST Grunt G</b> to be used under acrylic and siloxane protective coat ready to use liquid. Apply in one or two layers, it is possible to dilute second layer with water 1:1</li> </ul>	<p>0.08 - 0.10</p> <p>0.05 - 0.17</p> <p>0.05 - 0.25</p>	-
<b>Protective coats</b>	<b>Only to be used with finishing coats FAST Baranek. FAST Kornik and FAST MS</b>		
	<ul style="list-style-type: none"> <li>- <b>FAST F - S</b> silicate protective coat ready to use liquid, two layers, dilute up to 5 % of volume with FAST Grunt S</li> <li>- <b>FAST Silikon</b> silicone protective coat, ready to use liquid. one or two layers, first layer to be diluted up to 10 % of volume with water</li> <li>- <b>FAST SI-SI</b> siloxane protective coat. ready to use liquid, one or two layers, first layer to be diluted up to 10 % of volume with water</li> <li>- <b>FAST F-AZ</b> acrylic protective coat. ready to use liquid, one or two layers, first layer to be diluted up to 10 % of volume with water</li> </ul>	<p>0.10 - 0.20 (l/m<sup>2</sup>) per layer</p> <p>0.12 (l/m<sup>2</sup>) per layer</p> <p>0.10 - 0.20 (l/m<sup>2</sup>) per layer</p> <p>0.10 - 0.20 (l/m<sup>2</sup>) per layer</p>	-
<b>Ancillary materials</b>	Remain under the manufacturer's responsibility		

## **2 Specification of the intended use(s) in accordance with the applicable European Assessment Document (hereinafter "EAD")**

### **2.1 Intended use**

This ETICS is intended for use as external insulation of buildings' walls. The walls are made of masonry (bricks, blocks, stones ...) or concrete (cast on site or as prefabricated panels). The characteristics of the walls shall be verified prior to use of the ETICS, especially regarding conditions for reaction to fire classification and for fixing of the ETICS either by bonding or mechanically. The ETICS is designed to give the wall to which it is applied satisfactory thermal insulation.

The ETICS is made of non load-bearing construction elements. It does not contribute directly to the stability of the wall on which it is installed, but it can contribute to durability by providing enhanced protection from the effect of weathering.

The ETICS can be used on new or existing (retrofit) vertical walls. It can also be used on horizontal or inclined surfaces which are not exposed to precipitation.

The ETICS is not intended to ensure the airtightness of the building structure.

The choice of the method of fixing depends on the characteristics of the substrate, which may need preparation (see cl. 7.2.1 of the ETAG 004) and shall be done in accordance with the national instructions.

The ETICS belong to Category S/W2, according to EOTA Technical Report No 034.

### **2.2 Manufacturing**

The European Technical Assessment is issued for the ETICS on the basis of agreed data/information, deposited with the Technical and Test Institute Prague, which identifies the ETICS that has been assessed and judged. Changes to the ETICS or production process, which could result in this deposited data/information being incorrect, shall be notified to the Technical and Test Institute Prague before the changes are introduced. The Technical and Test Institute Prague will decide whether or not such changes affect the ETA and consequently the validity of the CE marking on the basis of the ETA and if so whether further assessment or alterations to the ETA, shall be necessary.

### **2.3 Design and installation**

The installation instructions including special installation techniques and provisions for the qualification of the personnel are given in the manufacturer's technical documentation.

Design, installation and execution of ETICS are to be in conformity with national documents. Such documents and the level of their implementation in Member States' legislation are different. Therefore, the assessment and declaration of performance are done taking into account general assumptions introduced in the chapters 7.1 and 7.2 of ETAG 004 used as EAD, which summarize how information introduced in the ETA and related documents is intended to be used in the construction process and gives advice to all parties interested when normative documents are missing.

## **2.4 Packaging, transport and storage**

The information on packaging, transport and storage is given in the manufacturer's technical documentation. It is the responsibility of the manufacturer(s) to ensure that this information is made know to the concerned people.

## **2.5 Use, maintenance and repair**

The finishing coat shall normally be maintained in order to fully preserve the ETICS performance. Maintenance includes at least:

- visual inspection of the ETICS,
- repairing of localized damaged areas due to accidents,
- the aspect maintenance with products adapted and compatible with the ETICS (possibly after washing or ad hoc preparation).

Necessary repairs should be performed as soon as the need has been identified.

It is important to be able to carry out maintenance as far as possible using readily available products and equipment, without spoiling appearance. Only products which are compatible with the ETICS shall be used.

The information on use, maintenance and repair is given in the manufacturer's technical documentation. It is the responsibility of the manufacturer(s) to ensure that this information is made know to the concerned people.

### 3 Performance of the product and references to the methods used for its assessment

The performances of the kit as described in this chapter are valid provided that the components of the kit comply with Annexes 1 - 4.

#### 3.1 Mechanical resistance and stability (BWR 1)

Not relevant.

#### 3.2 Safety in case of fire (BWR 2)

##### 3.2.1 Reaction to fire (ETAG 004 - clause 5.1.2.1, EN 13501-1)

Table No. 2

Configuration	Organic content / heat of combustion	Flame retardant content	Euroclass according to EN 13501-1
<b>Reaction to fire valid for general use of ETICS</b>			
Adhesive	max. 4.81 MJ/kg	No flame retardant	<b>B – s1, d0</b>
Panels of expanded polystyrene EPS Maximal density of 15 kg/m <sup>3</sup>	In quantity ensuring Euroclass E according to EN 13501-1	In quantity ensuring Euroclass E according to EN 13501-1	
Base coat render	max. 0.13 MJ/kg	No flame retardant	
Glass fiber mesh	max. 8.32 MJ/kg	No flame retardant	
Finishing coats with mineral binder Finishing coats with acrylic binder - except finishing coat fast granit Finishing coats with silicate binder Finishing coats with siloxane binder Finishing coats with silicone binder	max. 2.30 MJ/kg	No flame retardant	
<b>Reaction to fire valid only for ETICS in lower part of wall</b>			
Adhesive FAST Normal S FAST Specjal/FAST Specjal M	max. 0.14 MJ/kg	No flame retardant	<b>B – s1, d0</b>
Panels of expanded polystyrene EPS Maximal density of 36 kg/m <sup>3</sup>	In quantity ensuring Euroclass E according to EN 13501-1	In quantity ensuring Euroclass E according to EN 13501-1	
Base coat render	max. 0.13 MJ/kg	No flame retardant	

Configuration	Organic content / heat of combustion	Flame retardant content	Euroclass according to EN 13501-1
Glass fiber mesh	max. 8.32 MJ/kg	No flame retardant	
Finishing coat FAST Granit	max. 2.90 MJ/kg	No flame retardant	

Note: A European reference fire scenario has not been laid down for facades. In some Member States, the classification of ETICS according to EN 13501-1 might not be sufficient for the use in facades. An additional assessment of ETICS according to national provisions (e.g. on the basis of a large scale test) might be necessary to comply with Member State regulations, until the existing European classification system has been completed.

### 3.3 Hygiene, health and environment (BWR 3)

#### 3.3.1 Water absorption (ETAG 004 - clause 5.1.3.1)

- Base coat **FAST Specjal / FAST Specjal M:**

Water absorption after 1 hour < 1 kg/m<sup>2</sup>

Water absorption after 24 hours < 0.5 kg/m<sup>2</sup>

- Rendering system:

Table No. 3

		Water absorption after 24 hours	
		< 0.5 kg/m <sup>2</sup>	≥ 0.5 kg/m <sup>2</sup>
<b>Rendering system:</b> Base coat <b>FAST Specjal / FAST Specjal M</b> + finishing coats as indicated here:	<b>FAST Baranek</b> with protection coats FAST F-S, FAST F-AZ, FAST Silikon	X	
	<b>FAST Baranek</b> with protection coat FAST SI-SI		X
	<b>FAST Kornik</b>	X	
	<b>FAST WD (WET, DRY Dash)</b>	X	
	<b>FAST MS</b>	X	
	<b>FAST Baranek S</b> <b>FAST Kornik S</b>	X	
	<b>FAST Baranek A</b> <b>FAST Akryl +</b> <b>FAST Kornik A</b> <b>FAST Granit</b>		X
	<b>FAST Baranek SI</b> <b>FAST Kornik SI</b>		X

	FAST Baranek SIL FAST Kornik SIL		X
--	-------------------------------------	--	---

### 3.3.2 Watertightness (ETAG 004 - clause 5.1.3.2)

#### 3.3.2.1 Hygrothermal behavior

Pass (without defects).

#### 3.3.2.2 Freeze-thaw behaviour

Pass (without defects).

### 3.3.3 Impact resistance (ETAG 004 - clause 5.1.3.3)

Table No. 4

Rendering system: Base coat <b>FAST Specjal / FAST Specjal M</b> + reinforcement and finishing coats indicated hereafter:	Single standard mesh	Double standard mesh
<b>FAST Baranek</b> <b>FAST Kornik</b>	Category III	Category III for particle size 1.0 and 1.5 mm
		Category I for particle size $\geq 2.0$ mm
<b>FAST WD (WET, DRY Dash)</b>	Category I	NPD
<b>FAST MS</b>	Category III	Category I
<b>FAST Baranek S</b> <b>FAST Kornik S</b>	Category III	Category I
<b>FAST Baranek A</b> <b>FAST Akryl +</b> <b>FAST Kornik A</b>	Category III	Category III for particle size 1.0 and 1.5 mm
		Category I for particle size $\geq 2$ mm
<b>FAST Granit</b>	Category III	Category I
<b>FAST Baranek SI</b> <b>FAST Kornik SI</b>	Category III	Category I
<b>FAST Baranek SIL</b> <b>FAST Kornik SIL</b>	Category III	Category III for particle size 1.0 and 1.5 mm
		Category I for particle size $\geq 2$ mm

### 3.3.4 Water vapour permeability (ETAG 004 - clause 5.1.3.4)

Table No. 5

Rendering system: Base coat <b>FAST Specjal / FAST Specjal M</b> + reinforcement and finishing coats ,indicated hereafter	Equivalent air layer thickness $s_d$	
	Single standard mesh	Double standard mesh
<b>FAST Baranek</b> <b>FAST Kornik</b>	≤ 0,23 m	≤ 0,27 m
<b>FAST WD (WET, DRY Dash)</b>	≤ 0,44 m	NPD
<b>FAST MS</b>	≤ 0,45 m	≤ 0,51 m
<b>FAST Baranek S</b> <b>FAST Kornik S</b>	≤ 0,29 m	≤ 0,38 m
<b>FAST Baranek A</b> <b>FAST Akryl +</b> <b>FAST Kornik A</b>	≤ 0,38 m	≤ 0,55 m
<b>FAST Granit</b>	≤ 0,34 m	≤ 0,48 m
<b>FAST Baranek SI</b> <b>FAST Kornik SI</b>	≤ 0,32 m	≤ 0,39 m
<b>FAST Baranek SIL</b> <b>FAST Kornik SIL</b>	≤ 0,29 m	≤ 0,36 m

### 3.3.5 Release of dangerous substances (ETAG 004 - clause 5.1.3.5, EOTA TR034)

NPD (no performance determined).

## 3.4 Safety and accessibility in use (BWR 4)

### 3.4.1 Bond strength between base coat and insulation product (ETAG 004 - clause 5.1.4.1.1)

Bonding strength of base coat to insulation product ≥ 0.08 MPa (cohesive failure).

### 3.4.2 Bond strength between adhesive and substrate / insulation product (ETAG 004 - clauses 5.1.4.1.2, 5.1.4.1.3)

Table No. 6

		Initial state	48 hrs. immersion in water + 2 hrs. 23°C/50% RH	48 hrs. immersion in water + 7 days 23°C/50% RH
<b>FAST Normal S</b>	Concrete	≥ 0.25 MPa	≥ 0.08 MPa	≥ 0.25 MPa

<b>FAST Specjal/FAST Specjal M FAST Specjal DS</b>	Expanded polystyrene (EPS)	≥ 0.08 MPa	≥ 0.03 MPa	≥ 0.08 MPa
--	----------------------------	------------	------------	------------

### 3.4.3 Fixing strength (ETAG 004 - clause 5.1.4.2)

Test not required (no limitation of ETICS length).

### 3.4.4 Wind load resistance (ETAG 004 - clause 5.1.4.3)

Table No. 7

Anchor description	Trade name		See Annex No. 2	
			Surface assembly	Countersunk assembly
	Plate diameter (mm)		60 or more	60 or more
EPS characteristics	Thickness (mm)		≥ 50	≥ 100
	Tensile strength (kPa)		≥ 100	≥ 100
Maximal load	Anchors placed at the body of the insulation product	$R_{panel}$	min. value: 0.45 kN mean value: 0.47 kN	
	Anchors placed at joints of the insulation product	$R_{joint}$	min. value: 0.37 kN mean value: 0.41 kN	

### 3.4.5 Render strip tensile test

Table No. 8

		Glass fiber mesh <b>AKE 145 A / R 117 A101</b> (manufacturer: SAINT-GOBAIN ADFORS CZ s.r.o.)					
		Crack width $W_{typ}$ [mm]/ number of cracks at relative elongation $\epsilon$					
Load direction		$\epsilon = 0.3 \%$	$\epsilon = 0.5 \%$	$\epsilon = 0.8 \%$	$\epsilon = 1.0 \%$	$\epsilon = 1.5 \%$	$\epsilon = 2.0 \%$
Warp	Sample No. 1	-	-	≤ 0.05/2	≤ 0.05/4	≤ 0.05/9	≤ 0.10/11
	Sample No. 2	-	≤ 0.05/2	≤ 0.05/4	≤ 0.05/7	≤ 0.10/9	≤ 0.10/9
	Sample No. 3	-	-	≤ 0.05/3	≤ 0.05/6	≤ 0.10/10	≤ 0.10/12
Weft	Sample No. 1	-	-	≤ 0.05/4	≤ 0.05/6	≤ 0.05/8	≤ 0.05/13
	Sample No. 2	-	-	≤ 0.05/3	≤ 0.05/5	≤ 0.05/6	≤ 0.05/11
	Sample No. 3	-	-	≤ 0.05/4	≤ 0.05/5	≤ 0.05/7	≤ 0.05/13

Table No. 9

		Glass fiber mesh <b>AKE 160 A / R 131 A101</b> (manufacturer: SAINT-GOBAIN ADFORS CZ s.r.o.)					
		<b>Crack width <math>W_{typ}</math> [mm]/ number of cracks at relative elongation <math>\varepsilon</math></b>					
<b>Load direction</b>		$\varepsilon = 0.3 \%$	$\varepsilon = 0.5 \%$	$\varepsilon = 0.8 \%$	$\varepsilon = 1.0 \%$	$\varepsilon = 1.5 \%$	$\varepsilon = 2.0 \%$
Warp	Sample No. 1	-	-	$\leq 0.05/2$	$\leq 0.05/2$	$\leq 0.05/5$	$\leq 0.05/6$
	Sample No. 2	-	-	$\leq 0.05/1$	$\leq 0.05/1$	$\leq 0.05/3$	$\leq 0.05/5$
	Sample No. 3	-	-	$\leq 0.05/2$	$\leq 0.05/2$	$\leq 0.05/4$	$\leq 0.05/7$
Weft	Sample No. 1	-	$\leq 0.05/3$	$\leq 0.05/3$	$\leq 0.05/6$	$\leq 0.05/8$	$\leq 0.10/9$
	Sample No. 2	-	$\leq 0.05/3$	$\leq 0.05/5$	$\leq 0.05/5$	$\leq 0.05/9$	$\leq 0.10/10$
	Sample No. 3	-	$\leq 0.05/3$	$\leq 0.05/3$	$\leq 0.05/6$	$\leq 0.05/8$	$\leq 0.10/10$

Table No. 10

		Glass fiber mesh <b>117 S</b> (manufacturer: Technical Textiles, s.r.o.)					
		<b>Crack width <math>W_{typ}</math> [mm]/ number of cracks at relative elongation <math>\varepsilon</math></b>					
<b>Load direction</b>		$\varepsilon = 0.3 \%$	$\varepsilon = 0.5 \%$	$\varepsilon = 0.8 \%$	$\varepsilon = 1.0 \%$	$\varepsilon = 1.5 \%$	$\varepsilon = 2.0 \%$
Warp	Sample No. 1	-	$\leq 0.05/2$	$\leq 0.05/3$	$\leq 0.05/4$	$\leq 0.05/6$	$\leq 0.05/9$
	Sample No. 2	-	$\leq 0.05/3$	$\leq 0.05/5$	$\leq 0.05/5$	$\leq 0.10/7$	$\leq 0.10/9$
	Sample No. 3	-	$\leq 0.05/2$	$\leq 0.05/4$	$\leq 0.05/5$	$\leq 0.10/6$	$\leq 0.10/8$
Weft	Sample No. 1	-	$\leq 0.05/3$	$\leq 0.05/4$	$\leq 0.05/4$	$\leq 0.05/5$	$\leq 0.05/9$
	Sample No. 2	-	$\leq 0.05/1$	$\leq 0.05/2$	$\leq 0.05/3$	$\leq 0.05/6$	$\leq 0.10/9$
	Sample No. 3	-	$\leq 0.05/1$	$\leq 0.05/3$	$\leq 0.05/3$	$\leq 0.05/5$	$\leq 0.10/8$

Table No. 11

		<b>SECCO E 145</b> (manufacturer: ASGLATEX Ohorn GmbH)					
		<b>Crack width <math>W_{typ}</math> [mm]/ number of cracks at relative elongation <math>\varepsilon</math></b>					
<b>Load direction</b>		$\varepsilon = 0.3 \%$	$\varepsilon = 0.5 \%$	$\varepsilon = 0.8 \%$	$\varepsilon = 1.0 \%$	$\varepsilon = 1.5 \%$	$\varepsilon = 2.0 \%$
Warp	Sample No. 1	$\leq 0.05/3$	$\leq 0.05/4$	$\leq 0.05/8$	$\leq 0.05/12$	$\leq 0.05/12$ $\leq 0.10/1$	$\leq 0.05/12$ $\leq 0.10/3$
	Sample No. 2	$\leq 0.05/1$	$\leq 0.05/2$	$\leq 0.05/5$	$\leq 0.05/9$	$\leq 0.05/10$ $\leq 0.10/2$	$\leq 0.05/13$ $\leq 0.10/2$
	Sample No. 3	$\leq 0.05/2$	$\leq 0.05/3$	$\leq 0.05/6$	$\leq 0.05/10$	$\leq 0.05/11$ $\leq 0.10/2$	$\leq 0.05/12$ $\leq 0.10/3$
Weft	Sample No. 1	$\leq 0.05/2$	$\leq 0.05/5$	$\leq 0.05/6$	$\leq 0.05/10$ $\leq 0.10/1$	$\leq 0.05/14$ $\leq 0.10/1$	$\leq 0.05/13$ $\leq 0.10/3$
	Sample No. 2	$\leq 0.05/1$	$\leq 0.05/6$	$\leq 0.05/8$ $\leq 0.10/1$	$\leq 0.05/11$ $\leq 0.10/2$	$\leq 0.05/13$ $\leq 0.10/3$	$\leq 0.05/14$ $\leq 0.10/3$ $\leq 0.15/2$
	Sample No. 3	$\leq 0.05/2$	$\leq 0.05/5$	$\leq 0.05/7$ $\leq 0.10/2$	$\leq 0.05/10$ $\leq 0.10/3$	$\leq 0.05/12$ $\leq 0.10/3$	$\leq 0.05/15$ $\leq 0.10/2$ $\leq 0.15/1$

Table No. 12

		<b>SECCO E 160</b> (manufacturer: ASGLATEX Ohorn GmbH)					
		<b>Crack width <math>W_{typ}</math> [mm]/ number of cracks at relative elongation <math>\varepsilon</math></b>					
<b>Load direction</b>		$\varepsilon = 0.3 \%$	$\varepsilon = 0.5 \%$	$\varepsilon = 0.8 \%$	$\varepsilon = 1.0 \%$	$\varepsilon = 1.5 \%$	$\varepsilon = 2.0 \%$
Warp	Sample No. 1	$\leq 0.05/3$	$\leq 0.05/4$	$\leq 0.05/6$	$\leq 0.05/8$	$\leq 0.05/10$ $\leq 0.10/1$	$\leq 0.05/12$ $\leq 0.10/2$
	Sample No. 2	$\leq 0.05/1$	$\leq 0.05/3$	$\leq 0.05/6$	$\leq 0.05/9$ $\leq 0.10/2$	$\leq 0.05/11$ $\leq 0.10/2$	$\leq 0.05/14$ $\leq 0.10/3$
	Sample No. 3	$\leq 0.05/2$	$\leq 0.05/3$	$\leq 0.05/6$	$\leq 0.05/8$ $\leq 0.10/1$	$\leq 0.05/12$ $\leq 0.10/2$	$\leq 0.05/13$ $\leq 0.10/4$
Weft	Sample No. 1	$\leq 0.05/2$	$\leq 0.05/3$	$\leq 0.05/6$	$\leq 0.05/7$ $\leq 0.10/1$	$\leq 0.05/9$ $\leq 0.10/2$	$\leq 0.05/11$ $\leq 0.10/2$
	Sample No. 2	$\leq 0.05/2$	$\leq 0.05/4$	$\leq 0.05/8$	$\leq 0.05/9$ $\leq 0.10/2$	$\leq 0.05/10$ $\leq 0.10/3$	$\leq 0.05/12$ $\leq 0.10/3$
	Sample No. 3	$\leq 0.05/2$	$\leq 0.05/5$	$\leq 0.05/6$	$\leq 0.05/8$ $\leq 0.10/1$	$\leq 0.05/10$ $\leq 0.10/2$	$\leq 0.05/13$ $\leq 0.10/3$

Table No. 13

		<b>REDNET E 145</b> (manufacturer: ASGLATEX Ohorn GmbH)					
		<b>Crack width <math>W_{typ}</math> [mm]/ number of cracks at relative elongation <math>\varepsilon</math></b>					
<b>Load direction</b>		$\varepsilon = 0.3 \%$	$\varepsilon = 0.5 \%$	$\varepsilon = 0.8 \%$	$\varepsilon = 1.0 \%$	$\varepsilon = 1.5 \%$	$\varepsilon = 2.0 \%$
Warp	Sample No. 1	$\leq 0.05/3$	$\leq 0.05/4$	$\leq 0.05/8$	$\leq 0.05/12$	$\leq 0.05/12$ $\leq 0.10/1$	$\leq 0.05/12$ $\leq 0.10/3$
	Sample No. 2	$\leq 0.05/1$	$\leq 0.05/2$	$\leq 0.05/5$	$\leq 0.05/9$	$\leq 0.05/10$ $\leq 0.10/2$	$\leq 0.05/13$ $\leq 0.10/2$
	Sample No. 3	$\leq 0.05/2$	$\leq 0.05/3$	$\leq 0.05/6$	$\leq 0.05/10$	$\leq 0.05/11$ $\leq 0.10/2$	$\leq 0.05/12$ $\leq 0.10/3$
Weft	Sample No. 1	$\leq 0.05/2$	$\leq 0.05/5$	$\leq 0.05/6$	$\leq 0.05/10$ $\leq 0.10/1$	$\leq 0.05/14$ $\leq 0.10/1$	$\leq 0.05/13$ $\leq 0.10/3$
	Sample No. 2	$\leq 0.05/1$	$\leq 0.05/6$	$\leq 0.05/8$ $\leq 0.10/1$	$\leq 0.05/11$ $\leq 0.10/2$	$\leq 0.05/13$ $\leq 0.10/3$	$\leq 0.05/14$ $\leq 0.10/3$ $\leq 0.15/2$
	Sample No. 3	$\leq 0.05/2$	$\leq 0.05/5$	$\leq 0.05/7$ $\leq 0.10/2$	$\leq 0.05/10$ $\leq 0.10/3$	$\leq 0.05/12$ $\leq 0.10/3$	$\leq 0.05/15$ $\leq 0.10/2$ $\leq 0.15/1$

Table No. 14

		<b>REDNET E 160</b> (manufacturer: ASGLATEX Ohorn GmbH)					
		<b>Crack width <math>W_{typ}</math> [mm]/ number of cracks at relative elongation <math>\varepsilon</math></b>					
<b>Load direction</b>		$\varepsilon = 0.3 \%$	$\varepsilon = 0.5 \%$	$\varepsilon = 0.8 \%$	$\varepsilon = 1.0 \%$	$\varepsilon = 1.5 \%$	$\varepsilon = 2.0 \%$
Warp	Sample No. 1	$\leq 0.05/3$	$\leq 0.05/4$	$\leq 0.05/6$	$\leq 0.05/8$	$\leq 0.05/10$ $\leq 0.10/1$	$\leq 0.05/12$ $\leq 0.10/2$
	Sample No. 2	$\leq 0.05/1$	$\leq 0.05/3$	$\leq 0.05/6$	$\leq 0.05/9$ $\leq 0.10/2$	$\leq 0.05/11$ $\leq 0.10/2$	$\leq 0.05/14$ $\leq 0.10/3$
	Sample No. 3	$\leq 0.05/2$	$\leq 0.05/3$	$\leq 0.05/6$	$\leq 0.05/8$ $\leq 0.10/1$	$\leq 0.05/12$ $\leq 0.10/2$	$\leq 0.05/13$ $\leq 0.10/4$
Weft	Sample No. 1	$\leq 0.05/2$	$\leq 0.05/3$	$\leq 0.05/6$	$\leq 0.05/7$ $\leq 0.10/1$	$\leq 0.05/9$ $\leq 0.10/2$	$\leq 0.05/11$ $\leq 0.10/2$
	Sample No. 2	$\leq 0.05/2$	$\leq 0.05/4$	$\leq 0.05/8$	$\leq 0.05/9$ $\leq 0.10/2$	$\leq 0.05/10$ $\leq 0.10/3$	$\leq 0.05/12$ $\leq 0.10/3$
	Sample No. 3	$\leq 0.05/2$	$\leq 0.05/5$	$\leq 0.05/6$	$\leq 0.05/8$ $\leq 0.10/1$	$\leq 0.05/10$ $\leq 0.10/2$	$\leq 0.05/13$ $\leq 0.10/3$

Table No. 15

		Glass fiber mesh <b>Valmieras SSA-1363-160</b> (manufacturer: JSC Valmieras Stikla Šķiedra)					
		Crack width $W_{typ}$ [mm]/ number of cracks at relative elongation $\varepsilon$					
Load direction		$\varepsilon = 0.3 \%$	$\varepsilon = 0.5 \%$	$\varepsilon = 0.8 \%$	$\varepsilon = 1.0 \%$	$\varepsilon = 1.5 \%$	$\varepsilon = 2.0 \%$
Warp	Sample No. 1	$\leq 0.05/2$	$\leq 0.05/4$	$\leq 0.05/6$	$\leq 0.05/8$ $\leq 0.10/1$	$\leq 0.05/8$ $\leq 0.10/3$	$\leq 0.05/11$ $\leq 0.10/4$
	Sample No. 2	$\leq 0.05/1$	$\leq 0.05/3$	$\leq 0.05/5$	$\leq 0.05/6$	$\leq 0.05/10$ $\leq 0.10/1$	$\leq 0.05/12$ $\leq 0.10/3$
	Sample No. 3	$\leq 0.05/1$	$\leq 0.05/3$	$\leq 0.05/4$	$\leq 0.05/6$ $\leq 0.10/1$	$\leq 0.05/9$ $\leq 0.10/4$	$\leq 0.05/12$ $\leq 0.10/5$
Weft	Sample No. 1	$\leq 0.05/1$	$\leq 0.05/2$	$\leq 0.05/4$	$\leq 0.05/6$	$\leq 0.05/7$	$\leq 0.05/10$ $\leq 0.10/3$
	Sample No. 2	-	$\leq 0.05/3$	$\leq 0.05/5$	$\leq 0.05/6$	$\leq 0.05/9$ $\leq 0.10/1$	$\leq 0.05/11$ $\leq 0.10/2$
	Sample No. 3	$\leq 0.05/3$	$\leq 0.05/5$	$\leq 0.05/6$	$\leq 0.05/8$	$\leq 0.05/9$ $\leq 0.10/1$	$\leq 0.05/12$ $\leq 0.10/3$

The characteristic crack width  $W_{rk}$  [mm] at a render strain value of 0.8%, determined with simple Method II pursuant to ETAG 004, cl. 5.5.4.1.

Table No. 16

	Characteristic width of cracks $W_{rk}$ [mm] at render strain value of 0,8%	
	Warp direction	Weft direction
<b>AKE 145 A / R117 A101</b>	0,050	0,050
<b>AKE 160 A / R131 A101</b>	0,050	0,050
<b>117S</b>	0,050	0,050
<b>SECCO E 145</b>	0,050	0,109
<b>SECCO E 160</b>	0,050	0,050
<b>REDNET E 145</b>	0,050	0,109
<b>REDNET E 160</b>	0,050	0,050
<b>Valmieras SSA-1363-160</b>	0,050	0,050

### 3.5 Protection against noise (BWR 5)

#### 3.5.1 Airborne sound insulation

Table No. 17

Insulation product	Rendering system	ETICS fixing	Substrate description	ETICS performance
<p><b>Insulation product:</b> polystyrene Panels of expanded polystyrene</p> <p><b>Dimensions:</b> Length: 1000 mm Width: 500 mm Thickness: 50 mm</p> <p><b>Density:</b> 20 kg/m<sup>3</sup></p>	<p><b>Minimum mass of the rendering system:</b> 9.7 kg/m<sup>2</sup></p>	<p><b>Mechanical fixing:</b> anchor for ETICS ejothem STR U 2G 8 pcs/m<sup>2</sup></p> <p><b>Bonding by adhesives:</b> Fully bonded Coverage 2.0 kg/ m<sup>2</sup></p>	<p><b>Substrate:</b> Heavy masonry wall with rendering on both faces</p> <p><b>Density:</b> 305 kg/m<sup>2</sup></p>	<p><b><math>\Delta R_w = - 4\text{dB}</math></b></p> <p><b><math>\Delta R_w + C = - 4 \text{ dB}</math></b></p> <p><b><math>\Delta R_w + C_{tr} = - 3 \text{ dB}</math></b></p>

## 3.6 Energy economy and heat retention (BWR 6)

### 3.6.1 Thermal resistance

The thermal transmittance of the substrate wall covered by the ETICS is calculated in accordance with the standard EN ISO 6946:

$$U_c = U + \chi_p \times n$$

Where:

- $\chi_p \times n$  has only to be taken into account if it is greater than 0.04 W/(m<sup>2</sup>.K)
- $U_c$  global (corrected) thermal transmittance of the covered wall (W/ (m<sup>2</sup>.K))
- $n$  number of anchors (through insulation product) per 1 m<sup>2</sup>
- $\chi_p$  local influence of thermal bridge caused by an anchor. The values listed below can be taken into account if not specified in the anchor's ETA:
- = 0.002 W/K for anchors with a stainless steel screw covered by plastic anchors and for anchors with an air gap at the head of the screw  
( $\chi_p \times n$  negligible for  $n < 20$ )
  - = 0.004 W/K for anchors with a galvanized steel screw with the head covered by a plastic material  
( $\chi_p \times n$  negligible for  $n < 10$ )
  - = negligible for anchors with plastic nails (reinforced or not with glass fibres ...)
- $U$  thermal transmittance of the current part of the covered wall (excluding thermal bridges) (W/ (m<sup>2</sup>.K)) determined as follows:

$$U_c = \frac{1}{R_i + R_{render} + R_{substrate} + R_{se} + R_{si}}$$

Where:

- $R_i$  thermal resistance of the insulation product (according to declaration in reference to EN 13163) in (m<sup>2</sup>.K)/W
- $R_{render}$  thermal resistance of the rendering system (about 0.02 in (m<sup>2</sup>.K)/W) or determined by test according to EN 12667 or EN 12664
- $R_{substrate}$  thermal resistance of the substrate of the building (concrete, brick ...) in (m<sup>2</sup>.K)/W
- $R_{se}$  external superficial thermal resistance in (m<sup>2</sup>.K)/W
- $R_{si}$  internal superficial thermal resistance in (m<sup>2</sup>.K)/W

The value of thermal resistance of each insulation product shall be given in the manufacturer's documentation along with the possible range of thicknesses. In addition, the point thermal conductivity of anchors shall be given when anchors are used in the ETICS.

### 3.7 Sustainable use of natural resources (BWR 7)

NPD (no performance determined).

## 4 Assessment and verification of constancy of performance (hereinafter AVCP) system applied, with reference to its legal base

According to the European Commission decision 97/556/EC amended by the European Commission decision 2001/596/EC, the AVCP systems 1 and 2+ are valid (further described in Annex V to Regulation (EU) No. 305/2011).

Table No. 18

Product(s)	Intended use(s)	Level(s) or class(es) (Reaction to fire)	System(s)
External thermal insulation composite systems/kits (ETICS) with rendering	In external wall subject to fire regulations	A1 <sup>(1)</sup> , A2 <sup>(1)</sup> , B <sup>(1)</sup> , C <sup>(1)</sup>	1
		A1 <sup>(2)</sup> , A2 <sup>(2)</sup> , B <sup>(2)</sup> , C <sup>(2)</sup> , D, E, (A1 to E) <sup>(3)</sup> , F	2+
	In external wall not subject to fire regulations	Any	2+

<sup>(1)</sup> Products/materials for which a clearly identifiable stage in the production process results in an improvement of the reaction to fire classification (e.g. an addition of fire retardants or a limiting of organic material)

<sup>(2)</sup> Products/materials not covered by footnote (1)

<sup>(3)</sup> Products/materials that do not require to be tested for reaction to fire (e.g. Products/materials of Classes A1 according to Commission Decision 96/603/EC)

## 5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD:

In order to help the Notified Body to make an evaluation of conformity, the Technical Assessment Body issuing the ETA shall supply the information detailed below. This information together with the requirements given in EC Guidance Paper B will generally form the basis on which the factory production control (FPC) is assessed by the Notified Body.

This information shall initially be prepared or collected by the Technical Assessment Body and shall be agreed with the manufacturer. The following gives guidance on the type of information required:

1) ETA

Where confidentiality of information is required, this ETA makes reference to the manufacturer's technical documentation which contains such information.

2) Basic manufacturing proces

The basic manufacturing process is described in sufficient detail to support the proposed FPC methods.

The different components of the ETICS are generally manufactured using conventional techniques. Any critical process or treatment of the components which affects performance are highlighted in the manufacturer's documentation.

3) Product and materials specifications

The manufacturer's documentation includes:

- detailed drawings (possibly including manufacturing tolerances),
- incoming (raw) materials specifications and declarations,
- references to European and/or international standards,
- technical data sheets.

4) Control Plan (as a part of FPC)

The manufacturer and the Technical and Test Institute for Construction Prague have agreed a Control Plan which is deposited with the Technical and Test Institute for Construction Prague in documentation which accompanies the ETA. The Control Plan specifies the type and frequency of checks/tests conducted during production and on the final product. This includes the checks conducted during manufacture on properties that cannot be inspected at a later stage and for checks on the final product.

Products not manufactured by the ETICS manufacturer shall also be tested according to the Control Plan. It must be demonstrated to the Notified Body that the FPC system contains elements securing that the ETICS manufacturer takes products conforming to the Control Plan from his supplier(s).

Where materials/components are not manufactured and tested by the supplier in accordance with agreed methods, then where appropriate they shall be subject to suitable checks/tests by the ETICS manufacturer referring to the Control Plan once again.

In cases where the provisions of the European Technical Assessment and its Control Plan are no longer fulfilled, the Notified Body shall withdraw the certificate and inform the Technical and Test Construction Institute Prague without delay.

Issued in Prague on 27/05/2016

By

**Ing. Mária Schaan**

Head of the Technical Assessment Body

*Annexes:*

- Annex No. 1 : Insulation product characteristics
- Annex No. 2 : Anchors, description of individual product characteristics contained in the ETA
- Annex No. 3 : description of glass fiber mesh

## Annex No. 1 : Insulation product characteristics

Description and characteristics		Regulation	Declared characteristics of EPS boards	
			Class, level according to EN 13163	Value
Reaction to fire		EN 13501 -1	E	Apparent density $\leq 15 \text{ kg/m}^3$
Thermal resistance		EN 12667	Defined in CE mark in accordance with EN 13163	
Thickness		EN 823	T(2)	$\pm 2 \text{ mm}$
Length		EN 822	L(3)	$\pm 3 \text{ mm}$
Width			W(3)	$\pm 3 \text{ mm}$
Squareness		EN 824	S(5)	$\pm 5 \text{ mm/m}$
Flatness		EN 825	P(10)	10 mm
Surface		ETAG 004	Cut surface (homogenous, without coating)	
Dimensional stability	Under defined temperature and humidity conditions	EN 1604	DS(70,-)2	2%
	Under constant laboratory conditions	EN 1603	DS(N)2	$\pm 0.2\%$
Short term water absorption at partial immersion		EN 1609	---	$< 1 \text{ kg/m}^2$
Diffusion factor ( $\mu$ )		EN 13163	MU 20 – 40 MU 30 – 70	20 - 70
Tensile strength perpendicular to the faces of insulation product		EN 1607	TR100	$\geq 100 \text{ kPa}$
Shear strength		EN 12090	SS20	$\geq 20 \text{ kPa}$
Shear modulus of elasticity			GM1000	$\geq 1000 \text{ kPa}$

**Note:** Classes and levels for individual characteristics comply with EN 13163: 2012+A1:2015. Only insulation products of the same or better declared characteristics as stated in the table above can be used in this ETICS.

Reaction to fire E has to be proved for every insulation product also at 10 mm products thickness.

**Annex No. 2 : Anchors, description of individual product characteristics contained in the ETA**

Trade name	Plate diameter (mm)	Characteristic pull-out resistance	Plate stiffness (kN/mm)	Load at plate rupture (kN)
<b>Surface assembly</b>				
ejothem STR U, STR U 2G	60	see ETA - 04/0023	0.60	2.08
ejothem NT U	60	see ETA - 05/0009	0.60	2.43
ejothem NTK U	60	see ETA - 07/0026	0.50	1.44
EJOT SDM-T plus U	60	see ETA - 04/0064	0.70	2.24
EJOT H1 eco	60	see ETA - 11/0192	0.60	1.40
EJOT H3	60	see ETA - 14/0130	0.60	1.25
KOELNER TFIX-8M	60	see ETA - 07/0336	1.00	1.75
KOELNER TFIX-8S	60	see ETA - 11/0144	0.60	2.04
KOELNER KI-10N, KI-10NS	60	see ETA - 07/0221	0.30	1.39
BRAVOLL PTH-KZ 60/8-L <sub>a</sub>	60	see ETA – 05/0055	0.70	2.10
BRAVOLL PTH-60/8-L <sub>a</sub>			0.60	1.63
WKREŹ-MET-ŁFN ø8; ŁFM ø 8	60	see ETA -06/0080	0.50	1.04
WKREŹ-MET-ŁFN ø10; ŁFM ø10	60	see ETA -06/0105	0.40	1.00
WKREŹ-MET LTX 10, LMX 10	60	see ETA -08/0172	0.40	1.64
KEW TSD 8	60	see ETA - 04/0030	0.50	1.42
fischer TERMOZ 8N, 8 NZ	60	see ETA - 03/0019	0.50/0.50	1.34/1.43
fischer TERMOZ 8U, 8 UZ	60	see ETA - 02/0019	0.50/0.50	2.45/1.43
Hilti XI-FV	60	see ETA - 03/0004	0.40	1.60
Hilti SX-FV	60	see ETA - 03/0005	0.70	1.73
Hilti SD-FV 8	60	see ETA - 03/0028	0.30	1.55
Hilti SDK- FV 8	60	see ETA - 07/0302	0.50	1.48
Hilti D-FV, D-FV T	60	see ETA - 05/0039	0.80	1.93
<b>Countersunk assembly</b>				
ejothem STR U, STR U 2G	60	see ETA - 04/0023	0.60	2.08

**In addition to this list, anchors assessed in accordance with ETAG 014 can be used provided that such anchors meet the following requirements:**

	Requirements	
Plate diameter	≥ 60 mm	
Plate stiffness	Surface assembly:	≥ 0.3 kN/mm
	Countersunk assembly:	≥ 0.6 kN/mm
Rupture force of anchor's plate	≥ Higher of figures $R_{panel}$ and $R_{joint}$ in relevant table in Cl. 3.4.4	

### Annex No. 3 : description of glass fiber mesh

	Description	Strength after ageing	
	Standard fiber mesh applied in one or two layers with aperture size	Absolute strength after ageing (N/mm)	Relative residual strength after ageing, of the strength in the as-delivered state (%)
<b>AKE 145 A / R117 A101</b>	4,0 x 4,5 mm	≥ 20	≥ 50
<b>AKE 160 A / R131 A101</b>	3,5 x 3,8 mm	≥ 20	≥ 50
<b>117S</b>	4,6 x 3,2 mm	≥ 20	≥ 50
<b>SECCO E 145</b>	3,3 x 4,5 mm	≥ 20	≥ 50
<b>SECCO E 160</b>	3,5 x 3,8 mm	≥ 20	≥ 50
<b>REDNET E 145</b>	3,3 x 4,5 mm	≥ 20	≥ 50
<b>REDNET E 160</b>	3,5 x 3,8 mm	≥ 20	≥ 50
<b>Valmieras SSA-1363-160</b>	3,5 x 3,7 mm	≥ 20	≥ 50